

Bodenguard Q-300AS



Quartz sand 0.1-0.3mm

- » Easy mixing
- » Increases the coating volume

- » High hardness and durability

DESCRIPTION

BODENGUARD Q-300AS is an industrially processed quartz sand with graded particle size, which has undergone processing, cleaning and drying. It possesses high hardness and is characterized by chemical inertness, minimal moisture

absorption, and resistance to atmospheric pollution. It demonstrates exceptional abrasion resistance, remaining unchanged over time and under adverse weather conditions.

APPLICATION FIELD

The grain morphology allows the product to be mixed with cement, paints, or the **BODENGUARD** floor series from **KRAFT Paints** for increased volume in self-leveling coatings. The specific morphology

of the grains makes this product suitable for mixing with cement, with paints and especially with the **BODENGUARD SL-500 & BODENGUARD SL-550 Primer** from **KRAFT Paints**.

BODENGUARD Q-300AS

Quartz sand 0.1-0.3mm

TECHNICAL DATA

Composition		>98.5% SiO ₂
Appearance (Color)		Grey – Beige
Hardness (Mohs scale)		7
Density		2,65 g/cm ³ (±0,05)
Bulk density		1,40 g/cm ³ (±0,05)
Mixing ratio	Epoxy leveling mortar <1mm	SL-550 Primer 1:0.5 (w.w) Q-300AS
	Epoxy leveling mortar 1-2mm	SL-550 Primer 1:1 (w.w) Q-300AS
	Self-leveling epoxy topcoat	SL-500 1:0.5 (w.w) Q-300AS

PACKAGING

Available in 25 KG bags

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

Carefully read and follow all cautions and warnings on product label. For further information refer to the Safety Data Sheet for this product.

Poison Centre Telephone:

210 7793 777

STORAGE

Store in a dry environment at a temperature between 5°C and 35°C. Keep the packaging tightly sealed when not in use.

10/2026 THIS TECHNICAL DATA SHEET SUPERSEDES ALL PREVIOUS EDITIONS

2/2

DISCLAIMER: The above technical data, information, recommendations and guidance are based on scientific and technical knowledge, laboratory studies and long experience. However, the above information is considered to be as indicative and should be reviewed in any case in relation to each specific application conditions. Consequently, the suitability of each product in any application must be evaluated after referring to the updated Technical Data Sheet and to the website www.kraftpaints.com, as well as after contacting the technical support department, in case of necessity. Our company guarantees the quality of the product itself, whilst in any case the user/applicant is exclusively responsible for any undesirable failures after using the product.

DRUCKFARBEN HELLAS S.A.

ASPROPYRGOS 19 300, ATTIKA - GREECE | TEL.: +30 210 55 19 500 - FAX: +30 210 55 19 501
www.druckfarbengroup.com | www.kraftpaints.com



Toll-free number

800 111 7700 Monday - Friday, 8.00 am - 04.00 pm
 e-mail: paints.orders@druckfarben.gr